TALC ANALYSIS (ASBESTOS)

PRODUCT NUMBER 1615

PRODUCT ORIGIN Staly

D'ATE Supt. 30, 1972

LAB. REPORT NO.

CODE IDENTIFICATION

PRODUCT LOT NO. 921015

WORK PERFORMED BY Seymour Z. Lewin 71. Y. U.

INVOICE NO.

X-RAY DIFFRACTION ANALYSIS (PERCENT)

TREMOLITE

CHYSOTILE

ALPHA QUARTZ

CHLORITE

12

DOLOMITE

MAGNESITE

ND

NON-DETECTED

CURVE FILED IN FOLDER NO. 72/4



New York University

Department of Chemistry

4 Washington Place, Room 410
New York, N. V. 10003

New York, N.Y. 10003 Telephone: (212) 598-3427 7514

September |

Mr. George J. Dippold Whittaker, Clark and Daniels, Inc. 1000 Coolidge Street South Plainfield, New Jersey 07080

Dear Mr. Dippold:

The analysis of the four most recent talc samples you have sent me has just been completed, with the following results:

Sam	ple .		Talc	Chlorite	α-Quartz	Dolomite	Calcite	
No.	2450,	Lot #7390	77%	15%	n.d.	8%	n.d.	
No.	4608,	Lot #821708	70%	5%	2%	3%	20%	
No.	1615,	Lot #921015*	77%	12%	7%	2%	n.d.	X
No.	141,	Lot #82172	100%	n.d.	n.d.	n.d.	n.d.	

Sample No. 4608, Lot #821708 in the tabulation above showed some suspicious features in its x-ray diffraction pattern that might have been due to the presence of chrysotile. Therefore, this specimen was subjected to detailed examination by optical microscopy, and no chrysotile was found.

Sample No. 1615, Lot #921015 in the above tabulation showed some features in its x-ray pattern that suggested that it might contain some tremolite. Accordingly, this specimen was subjected to the detailed microscopic examination. Both tremolite and chrysotile fibers were found to be present in this sample. It is estimated that the tremolite content is about 2% by weight, and the chrysotile about 0.5%.

The protocol described above is that which the FDA is tentatively considering as their official testing procedure. That is, the talc is to be tested first by the continuous-scan x-ray diffraction method, and if nothing suspicious is observed in the pattern, it is considered acceptable. If there are any suspicious features, the talc is then to be examined by optical microscopy, to determine whether there are significant numbers of fibers visible which have the refractive indexes of the asbestos minerals.

Please note that the asbestos content of Talc No. 1615, Lot #92101 is just at the minimum level of detectability. It is evident that if this lot is blended with, e.g., Talc No. 141, Lot #82172, in the proportion of 1 part of the former to 2 parts of the latter, the resulting mixture will be fully acceptable by the analytical protocol described above.

Refer to report of 9/3/22 from N.y.V. Note statement an #1615 Tale - Lamy and I definitely semember This was followed up and suported as not being able to rependence resulto -Drul